



La marca del manejo forestal responsable



Laurel

Scientific name:
Cordia Alliodora



What's the tree like?

40-60ft in height, with diameters of 18-24"



Wood appearance

Heartwood is light brown and often variegated, sapwood creamy white. Grain can vary from fine to coarse, usually straight.



Shrinkage

Radial 3.4%
Tangential 7.1%
Volumetric 9.2%

Elastic Modulus

1,510,000 psi

Modulus of Rupture

12,180 psi.

Crushing Strength

6330 psi

0.45

Basic Specific Gravity

40

lbs/ft³

Average Dried Weight

1000

Janka hardness

www.agroforestal.co



DRYING

Air dries quickly with minimal checking or warping. Kiln drying schedules T6-D2(4/4), T3-D1(8/4)



WORKING PROPERTIES

Easy to work, finishes well, easily glued, stable during and after manufacture.



DURABILITY

Heartwood resists both white-rot and brown-rot fungi. Good resistance to dry-wood termites. Reported resistance to marine borers in Panama. Good weathering and moderate moisture absorption.



USES

Furniture and millwork. Boat building. General construction.

